

**DIAMOND HI-851 H.G.**

**Characteristics:**

- High impact, Good gloss,
- Low volatility
- Brilliant properties.

**Processing:**

- Extrusion Grade

**Applications:**

- Drinking cups, Refrigerator components, Cotton buds, Extrusion & Blow molding grade.

Material Status :

TYPICAL PROPERTIES	TEST METHOD	UNIT	VALUES
<b>Mechanical Properties</b>			
Tensile Strength at Yield / at break	ASTM D-638	kgf/cm <sup>2</sup>	250
Tensile Modulus	ASTM D-638		-
Tensile Elongation	ASTM D-638	%	60
Flexural Strength	ASTM D-790	kgf/cm <sup>2</sup>	450
Flexural Modulus	ASTM D-790		-
Izod Impact Strength	ASTM D-256	kgf-cm/cm	14
Gardner Falling Dart	ASTM D-1709	In-lb	130
<b>Thermal Properties</b>			
Vicat Softening Temp	ASTM D-1525	°C	100
Heat Distortion Temp	ASTM D-648	°C	90
<b>General Properties</b>			
Melt Flow Rate MFR 200/5	ASTM D-1238	gm/10 min	3.0
<b>Processing</b>			
Specific Gravity	ASTM D-792	23/23 °C	1.05
<b>Miscellaneous Properties</b>			
Gloss	ASTM D-523	%	80
Water Absorption		%	<0.1
Moisture Adsorption (23 C/50% r.h)		%	<0.1

<b>Product Description</b>	Diamond HI-851(H.G) is a High Impact Polystyrene grade with Opaque & Glossy surface. It gives excellent mechanical and heat resistance properties while providing with easy process ability and extrusion applications.
<b>Processing</b>	Although Polystyrene HI-851(H.G) can be processed by any method applicable to polystyrene based plastic, it is best suitable for Extrusion. The melt temperatures should not exceed 260 °C.
<b>Product Safety</b>	During processing of Polystyrene HI-851(H.G), small quantity of Styrene Monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm, no negative health effects are expected. In our experience, the concentration of styrene does not exceed 1 ppm in good ventilate workplace.
<b>Form supplied &amp; Storage</b>	Polystyrene HI-851(H.G) is supplied as cylindrical shaped granules. It has to be kept in its original containers in a dry, cool place, Avoid direct exposure to sunlight. Diamond HI-851(H.G) can also be stored in silos.
<b>Food Legislation</b>	If used unmodified and under appropriated processing conditions, Polystyrene HI-851(H.G) conforms with FDA title 21 CFR section 177.1640 regarding the use of in food contact articles. Diamond Polystyrene is also approved by PCSIR (Pakistan Council of Scientific & Industrial Research).
<b>Environmental</b>	Diamond polystyrene resins can be recycled , incinerated or disposed off in landfill without detriment to the environment. Adequate ventilation should be used during processing. Where recycling of Diamond Polystyrene is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Generally speaking, in the environment lost pellets are not a problem except under unusual circumstances – when they enter the Marine environment. They are inert and benign in terms of their physical environmental impact, but if ingested by waterfowl or aquatic life, they may mechanically cause adverse effects. Spills should be minimized and they should be cleaned up when they happen. Plastics should not be discarded into the Ocean or any other body of water.

**Note:**

The information & recommendations in this publications are, best of our knowledge, reliable, suggestions concerning used or applications are only the opinion of Pak Petrochemical Industries (Pvt.) Ltd. and users should perform their own test to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Pak Petrochemical MAKES NO WARRANT OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current standard specification statement herein, therefore should not be construed as representations or warranties.



*"Committed to Supply Quality Products"*